

Durain Inherent FR Ecogreen Work Pants

TILFRPT

DESCRIPTION

TIL Durain FR Work Pants with outstanding after-wash appearance. Features comfort fit, multiple pockets, and flame retardant construction with FR Aramid threads for durability.

KEY FEATURES

- Washable

DETAILED FEATURES

- Comfort Fit design for all-day wear
- 2 Side Pockets for tools and personal items
- Side Tool Pocket for easy access
- 2 Back Pockets with secure closure
- Stitched with FR Aramid Threads for durability
- Bar tack in all the Stress Points for reinforcement
- Elastic Waist Band adding flexibility and comfort
- Belt Loops for additional adjustment
- Outstanding after-wash appearance maintains professional look
- Comfort Fit
- Multiple pockets
- FR Aramid Threads
- Elastic Waist Band
- Multi-norm protection

APPLICATIONS

- Oil & Gas Industry
- Petrochemical work
- Electrical utilities
- Welding operations
- Flash fire hazard areas
- General FR work environments



Navy Blue Code: Nvy



OTHER COLORS



Sunrise Orange

PRODUCT INFORMATION

Category: Workwear

Available Sizes: 24, 26, 28, 30, 32, 34, 36, 38, 40, 42, 44, 46, 48, 50, 52, 54, 56, 58, 60

PACKAGING WASTE

Material	Type	Unit	Weight (g)	Length (mm)	Width (mm)	Height (mm)
Cardboard	Outer	1	0.05	0.716	0.232	0.414
Plastic	Inner	1	0.01	0.5	0.4	0.0
Paper	Inner	1	0.002	0.21	0.148	0.0



Durain Inherent FR Ecogreen Work Pants

TILFRPT

Technical Data

Parameter	Specification	Standard / Test Method
Product Code	TILFRPT	
Width	150 cm (+2/-1 cm)	ISO 3801:1978
Weight	200g/m ² (±5%)	ISO 3932:1980
Composition	Modacrylic/lyocell/para-aramid/Static-Control™	
Construction	2/1 twill	
Available finishes	Standard: Comfort. Optional: Hydro-Tec	

Physical Performance

Parameter	Specification	Standard / Test Method
Tensile Strength	700 N x 500 N (± 10%)	ISO 13934-1:1999
Tear Strength	40 N x 30 N (± 10%)	NEN-EN-ISO 13937-1:2000

Care Labelling

Parameter	Specification	Standard / Test Method
Domestic Laundering	 60°    	
Industrial Laundering	70°C	
PPE Requirements	   optional:  	

Certifications

Icon	Specification	Standard / Test Method
	Industrial flame and heat hazards	EN ISO 11611, 11612 A1, A2, B1, C1, E1, F1: 2015 (A1 + A2= 100 x ISO 15797 - 75°C)
	Short-duration thermal exposures from fire	NFPA 2112: 2018
	Electric Arc	Single Layer: EN IEC 61482-1-2, class 1; 2015 HRC/Category 1 (4 ≤ ATPV ≥ 8 cal/cm ²) System: XL9200 + XL9240 EN IEC 61482-1-2; 2015 class 2 (7kA) System: HRC/Category 2 (8 ≤ ATPV ≥ 25 cal/cm ²)
	Anti-Static for explosion risk	EN 1149-5: 2018, EN 1149-3: 2004
	Liquid chemicals **	EN 13034: 2005 + A1: 2009
	Contrast colours: Delftblue 89249, Twilight 89250	EN ISO 20471: 2013
	General requirements***	EN ISO 13688: 2013
	Öko-Tex Standard 100, class 2	Centexbel, no. 0903009



All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. PARKER Coverall declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.

